

7th of November, 2017


TA17108
 GEN0077

To Whom It May Concern,

RE: Adhesion testing - Amalfi Glass Mosaics

Mapei Technical Assistance Department has been requested by our Mr Steve Lawrence to perform adhesion testing on a glass mosaic tile provided by Amalfi.

Product Supplier	Amalfi
Type	Glass mosaic with mesh backing
Dimension (mm)	36 x 36
Colour	White and blue shades



Adhesive testing was conducted in accordance with the following AS ISO-13007-2 (2013) test methods:

- Adhesion strength (28 days),
- Adhesion strength after water immersion.

The results exceeded the minimum requirement of the standard and as such, the below adhesive are deemed satisfactory:

- **Keraflex Maxi S1**
- **Ultralite S1**
- **Kerabond Plus + Isolastic 50**
- **Keracolor FF + Planicrete SP**

Due to the mesh backing not allowing full adhesive contact with the back of tile, it is important to use an appropriate notched trowel and to push the sheet firmly into the fresh adhesive. Frequently check coverage when installing.

If you require any further assistance, please do not hesitate to contact MAPEI's Technical Department.

Kind regards,



Dalton Bryant BEng | Technical Engineer
Technical Assistance Department
 T. + 61 7 3276 5000
 Email: Technical-AU@mapei.com.au

DISCLAIMER: *This report provides guideline information only, it is not a general specification for the application/installation of the products described. Each project in fact may vary in relation to many parameters such as building condition, material used or exposure and the recommendations may vary according. Mapei Australia provides results based on laboratory tests and laboratory conditions in good faith and assumes no responsibility for technical inaccuracies or typographical errors. For specific applications/installations contact the Mapei Australia office.*

It must also be noted that the proprietary test sample is NOT a Mapei product and as such Mapei has no control over the formulation or the performance characteristics. The results stated in this report are specific only to the test sample Mapei received.